

Technical Data Sheet (TDS)

Silk PLA

ERYONE Silk PLA 3D Printing Lint boasts a satin-like, delicate, and lustrous metallic sheen. Its smooth, refined surface effectively conceals print textures, resulting in a seamless, glossy finish. The surface gloss can be flexibly controlled by adjusting the nozzle temperature and print speed—increasing the print temperature or slowing down the print speed further accentuates its mirror-like, translucent metallic sheen. This lint offers excellent printability, producing even, uniform, and smooth filament output without clogging. Compatible with 99% of 3D printing equipment on the market, it's the ideal choice for creating exquisite artworks, creative decorative pieces, or intricately detailed character models.

Part I: Suggests Printing Parameters

Parameter	Set up
Nozzle temperature	190-220 °C
Bed temperature	55-70°C
Bed material	glass, PEI, spring steel plate
Bottom printing temperature	190-220°C
Sealed printing	supports open printing, and the sealing effect is better if it is sealed
Printing speed	30-100mm/s
Drying conditions	50-60°C, 6h

Part II: Physical Properties of Materials

Property	Testing Method	Unit	Typical Value
Density(g/cm ³ at 21.5 ° C)	ASTM D792 (ISO 1183, GB/T 1033)	g/cm ³	1.32
Vicat Softening Temperature(° C)	ASTM D1525 (ISO 306 GB/T 1633)	°C	56
Heat distortion temperature(° C)	ASTM D648 0.45MPa	°C	53
Glass transition temperature (° C)	DSC, 10 ° C/min	°C	63
Melt Index(g/10 min)	220 ° C, 10kg 240 ° C, 2.16 kg	g/10min	20.5±1.5


Part III: Mechanical Properties of Printed Samples

Property	Test conditions	Test standards	unit	Typical Value
Tensile strength X-Y	50mm/min	GB/T 1040.4	MPa	55.2
Tensile modulus X-Y	50mm/min	GB/T 1040.1-2006	MPa	1215.4
Elongation at break X-Y	50mm/min	GB/T 1040.4	%	1.7
Tensile strength X-Z	50mm/min	GB/T 1843	MPa	12.1
Tensile modulus X-Z	50mm/min	GB/T 1040.1-2006	MPa	1051.9
Elongation at breakX-Z	50mm/min	GB/T 1040.4	%	1.2
Bending strength	2mm/min	GB/T 9341	MPa	83
Bending modulus	2mm/min	GB/T 9341	MPa	3006.8
Charpy Impact strenght	2.75J	GB/T 1043.1-2008	kJ/m2	2.83

Note: All splines are printed under the following conditions: printing temperature=220 ° C, printing speed=80mm/s, base plate 60 ° C, filling=100%, nozzle diameter=0.4mm


TENSILE TESTING SPECIMEN

ISO 527,GB/T 1040




FLEXURAL TESTING SPECIMEN

ISO 178,GB/T 9341



IMPACT TESTING SPECIMEN

ISO 179,GB/T 1043



Disclaimers

The values given in this data table are for reference and comparison only. They should not be used for design specifications or quality control. The actual value may vary depending on the printing conditions. The final performance of printed components depends not only on the material, but also on the component design, environmental conditions, printing conditions, and so on. Product specifications are subject to change without prior notice.